

SAN DECO®
Paint Manufacturing & Distribution

CAPPADOCIA PLASTER

Interior/Exterior Clay and Lime-Based Coating

CAPPADOCIA PLASTER is a surface coating developed for use on both interior and exterior surfaces. Its special combination of lime and clay allows a wide range of textured finishes. It is used together with its dedicated primer, finish and protective impregnation products.

WATER BASED · LOW VOC · TINTABLE

Cappadocia Plaster has a special filler structure containing clay and lime.

It is easy to apply and allows patterns and textures to be created with ease.

Thanks to its fibrous structure, it bridges cracks on the applied surfaces.

The thick film it can form during application easily covers defects and imperfections on the surface.

It is formulated to withstand exterior conditions.

Its high water vapour permeability allows moisture to escape and lets the surface breathe.

It is water-based and harmless to human health and the environment.

CONTENT: *Clay and lime-based, water-based*	PACKAGING: *25 KG*
THINNING: *Ready to use; do not dilute.*	DRYING TIME: *At 23 °C: Touch dry in 5–6 hours; full cure in 24–48 hours.*
PRIMER: *Cappadocia Primer*	FULLY DRY: *24–48 hours*
APPLICATION TOOL: *Trowel, brush, texture trowel, etc.*	COLORING:-
NUMBER of COATS: *Single or multi-layer*	VOC: *EU limit value (Directive 2004/42/EC)* *Category A/l: Decorative effect coatings (water-based): 200 g/l (2010)* *Cappadocia Plaster contains max. 0 g/l VOC*
STORAGE and SHELF LIFE: *Can be stored for up to 2 years in unopened original packaging, in a cool and dry place, protected from direct sunlight, at temperatures between +5 °C and +35 °C.*	

CONSUMPTION - Single Coat : *Consumption may vary depending on the type, absorbency, and structure of the surface, as well as the application techniques. For precise consumption, a controlled sample application should be performed.*

Consumption is 1–2 kg per m^2

APPLICATION AREA

Used as a coating material on walls, plaster, exposed concrete and wooden surfaces in interior and exterior areas, with its own primer after proper surface preparation.

SURFACE PREPARATION

After all dirt, grease, flaking paint and dust have been removed from the surface, surface irregularities should be levelled with San Deco Acrylic Fine Filler and the surface should be primed with Cappadocia Primer.

SURFACE CONDITION

The ambient temperature should be between a minimum of +5°C and a maximum of +35°C during application and for 24 hours afterwards.

The relative humidity should be below 75% during application.

The moisture content of the surface to be coated should be below 10%.

APPLICATION

Cappadocia Plaster can be applied in a single coat or in multiple layers, as desired.

It should be mixed until homogeneous and used without thinning.

It is applied with a steel trowel.

The application thickness can be adjusted to suit the desired design. Up to 3 cm can be applied in a single pass.

Textures can be created with any hand tool to suit the desired design.

The use of a finish is optional for interior applications; a clear or coloured finish is mandatory for exterior applications.

Likewise, protective impregnation is optional for interior applications; for exterior applications it is mandatory and must be applied after the finish.

It is recommended to use a single batch of product within the same project. Where more than one batch is used, the batches should be mixed together in equal proportions to avoid batch-related differences.

HAZARD & PRECAUTIONARY STATEMENTS

H314 Causes severe skin burns and eye damage.
P260 Do not breathe dust/fume/gas/mist/vapours/spray.
P264 Wash ... thoroughly after handling.
P280 Wear protective gloves/protective clothing/eye protection/face protection.
P301 + P330 + P331 IF SWALLOWED: rinse mouth. Do NOT induce vomiting.
P303 + P361 + P353 IF ON SKIN (or hair): Remove/Take off immediately all contaminated clothing. Rinse skin with water/shower.
P304 + P340 IF INHALED: Remove victim to fresh air and keep at rest in a position comfortable for breathing.
P305 + P351 + P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
P310 Immediately call a POISON CENTER or doctor/physician.
P321 Specific treatment (see ... on this label).
P405 Store locked up.

Note: For more information, please refer to the product's Safety Data Sheet (SDS).

This technical data sheet is based on laboratory data obtained under standard conditions. For details not sufficiently covered above, please consult technical personnel. The manufacturer cannot be held responsible for any errors resulting from insufficient information. Our company reserves the right to amend this information. For detailed information regarding health, safety, transport risks, and precautions, refer to the Material Safety Data Sheet (MSDS).

This product is manufactured by Deka Boya Sanayi ve Tic. A.Ş., certified under ISO 9001, ISO 14001, ISO 14064, ISO 45001, and ISO 27001 standards.